

## Coiled Tubing CT90 2.000

Designation		Wall Thickness		Mass per Unit Length	Calculated Inside Diameter	Tubing Area (Sq.in)		Tube Load Body		Internal Pressure (psi)		Collapse Strength	Internal Capacity per 1000ft		Torsional Yield	
		Specified	Min			W/min.	Internal min.	Yield min	Tensile min	Hydro Test 90%	Internal Yield min.					
OD	WT	inch	inch	lb/ft	inch	inch <sup>2</sup>	inch <sup>2</sup>	lb	lb	psig	psig	psig	gal	bar	ft.lbs	
2	2.000	0.109	0.109	0.104	2.20	1.782	0.619	2.522	58,300	62,800	8,300	9,200	5,600	129.48	3.08	2418
	2.000	0.118	0.118	0.113	2.37	1.764	0.670	2.472	62,800	67,700	8,900	9,900	6,700	126.87	3.02	2591
	2.000	0.125	0.125	0.118	2.51	1.750	0.698	2.444	66,300	71,400	9,500	10,600	7,800	124.87	2.97	2685
	2.000	0.134	0.134	0.127	2.67	1.732	0.747	2.394	70,700	76,200	10,100	11,200	8,900	122.31	2.91	2851
	2.000	0.145	0.145	0.138	2.88	1.710	0.807	2.334	76,100	82,000	11,100	12,300	10,500	119.23	2.84	3046
	2.000	0.156	0.156	0.148	3.08	1.688	0.861	2.280	81,300	87,700	12,000	13,300	12,200	116.18	2.77	3217
	2.000	0.175	0.175	0.167	3.41	1.650	0.962	2.180	90,300	97,300	13,100	14,600	13,600	111.01	2.64	3527
	2.000	0.188	0.188	0.180	3.64	1.624	1.029	2.112	96,300	103,800	14,000	15,600	14,500	107.53	2.56	3726
	2.000	0.204	0.204	0.194	3.92	1.592	1.101	2.041	103,600	111,600	15,300	17,000	15,700	103.34	2.46	3931
	2.000	0.224	0.224	0.214	4.25	1.552	1.201	1.941	112,500	121,200	16,700	18,600	17,100	98.21	2.34	4205
	2.000	0.250	0.250	0.240	4.68	1.500	1.327	1.815	123,700	133,300	18,700	20,800	19,000	91.74	2.19	4532
	2.000	0.276	0.276	0.266	5.09	1.448	1.449	1.693	134,500	145,000	20,200	22,400	20,300	85.49	2.04	4827
2.000	0.281	0.281	0.271	5.16	1.438	1.472	1.670	136,600	147,200	20,400	22,700	20,600	84.31	2.01	4880	

CT90 2.000

Jiangsu Tube Solution Co., Ltd.  
The other coiled tubing supplier

### Chemistry Composition

C,% 0.16 max Mn,% 1.20 max P,% 0.020 max S,% 0.005 max Si,% 0.50 max

Contact: sales@tubemfg.com

### Mechanical Properties

Tensile Strength: 97,000psi (669MPa) min

Yield Strength: 90,000psi (621MPa) min

Hardness: 22HRC max

Tensile strength & yield strength minimum are calculated on specified wall.

Other dimensions are available on request.